



Edgetek™ AT-30GF/000 BK004

Acetal (POM) Copolymer

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.62	1.62	ASTM D792
Molding Shrinkage - Flow	4.0E-3 to 0.010 in/in	0.40 to 1.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	14500 psi	100 MPa	ASTM D638
Flexural Modulus ³	1.07E+6 psi	7350 MPa	ASTM D790
Flexural Strength ³	23200 psi	160 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	0.84 ft·lb/in	45 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	320 °F	160 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	374 to 392 °F	190 to 200 °C
Middle Temperature	374 to 392 °F	190 to 200 °C
Front Temperature	374 to 392 °F	190 to 200 °C
Mold Temperature	167 to 185 °F	75 to 85 °C

Injection Notes
Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions.SM