



Edgetek™ ATC-000/000 1315 BLACK

Acetal (POM) Copolymer

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.41 g/cm ³	1.41 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	10 to 15 cm ³ /10min	10 to 15 cm ³ /10min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	421000 psi	2900 MPa	ISO 527-2
Tensile Stress (Yield)	8700 psi	60.0 MPa	ISO 527-2
Tensile Strain (Break)	15 %	15 %	ISO 527-2
Flexural Modulus	348000 psi	2400 MPa	ISO 178
Flexural Strength	8410 psi	58.0 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.9 ft·lb/in ²	4.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	No Break	No Break	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	212 °F	100 °C	ISO 75-2/A
Vicat Softening Temperature	302 °F	150 °C	ISO 306
Melting Temperature (DSC)	329 to 338 °F	165 to 170 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94
FMVSS Flammability	< 3.9 in/min	< 100 mm/min	DIN 75200

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	374 to 410 °F	190 to 210 °C
Mold Temperature	167 to 212 °F	75 to 100 °C

Notes

¹ Typical values are not to be construed as specifications.

² +/-0.02