



Edgetek™ ATC-000/000 IM15 Natural UV

Acetal (POM) Copolymer

Key Characteristics

General		
Material Status	• Commercial: Active	
Regional Availability	• Africa & Middle East	• Europe
Features	• Impact Modified	• UV Stabilized
Appearance	• Natural Color	
Processing Method	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.33 to 1.37 g/cm ³	1.33 to 1.37 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	5.00 to 7.00 cm ³ /10min	5.00 to 7.00 cm ³ /10min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	225000 psi	1550 MPa	ISO 527-2
Tensile Stress	5800 psi	40.0 MPa	ISO 527-2
Tensile Strain (Break)	> 40 %	> 40 %	ISO 527-2
Flexural Modulus	196000 psi	1350 MPa	ISO 178
Flexural Strength	8700 psi	60.0 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	6.7 ft·lb/in ²	14 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	No Break	No Break	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	275 °F	135 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	158 °F	70.0 °C	ISO 75-2/A
Vicat Softening Temperature	230 °F	110 °C	ISO 306
Melting Temperature (DSC)	329 to 338 °F	165 to 170 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94
FMVSS Flammability	< 3.9 in/min	< 100 mm/min	DIN 75200

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	374 to 410 °F	190 to 210 °C
Mold Temperature	167 to 212 °F	75 to 100 °C