



Edgetek™ ATC-30GF/000 Natural UV

Acetal (POM) Copolymer

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• UV Stabilized
Appearance	• Natural Color
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.57 to 1.61 g/cm ³	1.57 to 1.61 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.00 to 4.00 cm ³ /10min	2.00 to 4.00 cm ³ /10min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.25E+6 psi	8600 MPa	ISO 527-2
Tensile Strength	8700 psi	60.0 MPa	ISO 527-2
Tensile Stress (Break)	145 psi	1.00 MPa	ISO 527-2
Flexural Modulus	943000 psi	6500 MPa	ISO 178
Flexural Strength	13100 psi	90.0 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.1 ft·lb/in ²	4.5 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	11 ft·lb/in ²	24 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	320 °F	160 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	302 °F	150 °C	ISO 75-2/A
Vicat Softening Temperature	320 °F	160 °C	ISO 306
Melting Temperature (DSC)	329 to 338 °F	165 to 170 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB	UL 94
Glow Wire Flammability Index 0.13 in (3.2 mm)	1020 °F	550 °C	IEC 60695-2-12
FMVSS Flammability	< 3.9 in/min	< 100 mm/min	DIN 75200

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	374 to 410 °F	190 to 210 °C

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	167 to 212 °F	75 to 100 °C

Notes

¹ Typical values are not to be construed as specifications.



Beyond Polymers.

Better Business Solutions. SM