



Edgetek™ CY1000 GR188

Polycarbonate + ABS

Key Characteristics

Product Description	
Impact modified	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Additive	• Impact Modifier
Features	• Impact Modified
Appearance	• Grey
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13	ASTM D792
Molding Shrinkage - Flow	4.0E-3 to 6.0E-3 in/in	0.40 to 0.60 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	7250 psi	50.0 MPa	ASTM D638
Flexural Modulus ³	305000 psi	2100 MPa	ASTM D790
Flexural Strength ³	11600 psi	80.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	10 ft-lb/in	550 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	216 °F	102 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	ASTM D257

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	446 to 482 °F	230 to 250 °C
Middle Temperature	446 to 482 °F	230 to 250 °C
Front Temperature	446 to 482 °F	230 to 250 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (50 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions.SM