



Edgetek™ CY1000-10GF/000 FR V0 NC702

Polycarbonate + ABS

Key Characteristics

Product Description	
Non-halogen flame retardant	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Halogen Free
Appearance	• Natural Color
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.23	1.23	ASTM D792
Molding Shrinkage - Flow	3.0E-3 to 5.0E-3 in/in	0.30 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	10900 psi	75.0 MPa	ASTM D638
Flexural Modulus ³	609000 psi	4200 MPa	ASTM D790
Flexural Strength ³	17400 psi	120 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	2.2 ft-lb/in	120 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	248 °F	120 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	446 to 482 °F	230 to 250 °C
Middle Temperature	446 to 482 °F	230 to 250 °C
Front Temperature	446 to 482 °F	230 to 250 °C
Mold Temperature	158 to 194 °F	70 to 90 °C
Injection Notes		
Injection Pressure: MED-HIGH		
Hold Pressure: MED-HIGH		
Screw Speed: MODERATE		
Back Pressure: LOW		

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions.SM