



Edgetek™ EM01042076BG

Polycarbonate

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber
Features	• Flame Retardant
Appearance	• Green
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.27	1.27	ASTM D792
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	9430 psi	65.0 MPa	ASTM D638
Tensile Elongation ² (Break)	10 %	10 %	ASTM D638
Flexural Modulus ³	348000 psi	2400 MPa	ASTM D790
Flexural Strength ³	16000 psi	110 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	1.5 ft-lb/in	80 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	257 °F	125 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	V-0	V-0	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	230 to 266 °F	110 to 130 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Processing (Melt) Temp	536 to 590 °F	280 to 310 °C
Mold Temperature	176 to 248 °F	80 to 120 °C

Injection Notes
Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW