



Edgetek™ ET5200-5029 LD Black 70

Polypropylene Copolymer

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Features	• Good Heat Resistance • Good Impact Resistance • Good Stiffness	• Good Strength • Heat Stabilized • Low Density	• Low Flow • UV Stabilized
Uses	• Appliance Components • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0 g/10 min	3.0 g/10 min	ISO 1133
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	363000 psi	2500 MPa	ISO 527
Tensile Stress	4350 psi	30.0 MPa	ISO 527-2/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	3.8 ft·lb/in ²	8.0 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	320 to 329 °F	160 to 165 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	1.0 hr	1.0 hr
Rear Temperature	347 to 365 °F	175 to 185 °C
Middle Temperature	356 to 374 °F	180 to 190 °C
Front Temperature	365 to 383 °F	185 to 195 °C
Nozzle Temperature	383 to 392 °F	195 to 200 °C
Mold Temperature	77 to 131 °F	25 to 55 °C

Notes

¹ Typical values are not to be construed as specifications.

² 0.039 in/min (1.0 mm/min)