



## Edgetek™ MP-30GF/000 BLACK

### Polyphenylene Ether + PS

#### Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Black
Processing Method	• Injection Molding

#### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.29	1.29	ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 4.0E-3 in/in	0.10 to 0.40 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	1.05E+6 psi	7240 MPa	ASTM D638
Tensile Strength <sup>2</sup>	15500 psi	107 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	3.5 %	3.5 %	ASTM D638
Flexural Modulus <sup>3</sup>	1.09E+6 psi	7500 MPa	ASTM D790
Flexural Strength <sup>3</sup>	24700 psi	170 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	2.3 ft-lb/in	130 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	291 °F	144 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	Internal Method

#### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	194 to 212 °F	90 to 100 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	518 to 572 °F	270 to 300 °C
Middle Temperature	518 to 572 °F	270 to 300 °C
Front Temperature	518 to 572 °F	270 to 300 °C
Mold Temperature	149 to 203 °F	65 to 95 °C

#### Injection Notes

Injection Pressure: MED-HIGH  
Hold Pressure: MED-HIGH  
Screw Speed: MODERATE  
Back Pressure: LOW

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 0.20 in/min (5.0 mm/min)

<sup>3</sup> 0.051 in/min (1.3 mm/min)



*Beyond Polymers.*

*Better Business Solutions. SM*