



# Edgetek™ PC-20GF/000 NH FRV0 BLACK

## Polycarbonate

### Key Characteristics

#### Product Description

Glass Fiber Reinforced, Impact Modified, Non-halogen Containing Flame Retardant Polycarbonate Compound. UL listed.

#### General

|                        |                                  |
|------------------------|----------------------------------|
| Material Status        | • Commercial: Active             |
| Regional Availability  | • Asia Pacific                   |
| Filler / Reinforcement | • Glass Fiber                    |
| Features               | • Flame Retardant • Halogen Free |
| Appearance             | • Black                          |
| Processing Method      | • Injection Molding              |

### Technical Properties <sup>1</sup>

| Physical                                          | Typical Value (English) | Typical Value (SI) | Test Method |
|---------------------------------------------------|-------------------------|--------------------|-------------|
| Specific Gravity                                  | 1.34                    | 1.34               | ASTM D792   |
| Molding Shrinkage (0.118 in (3.00 mm))            | 0.20 to 0.50 %          | 0.20 to 0.50 %     | ISO 294-4   |
| Mechanical                                        | Typical Value (English) | Typical Value (SI) | Test Method |
| Tensile Strength <sup>2</sup>                     | 16700 psi               | 115 MPa            | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break)           | 3.0 %                   | 3.0 %              | ASTM D638   |
| Flexural Modulus <sup>3</sup>                     | 870000 psi              | 6000 MPa           | ASTM D790   |
| Flexural Strength <sup>3</sup>                    | 21800 psi               | 150 MPa            | ASTM D790   |
| Impact                                            | Typical Value (English) | Typical Value (SI) | Test Method |
| Notched Izod Impact                               |                         |                    | ASTM D256   |
| 73°F (23°C), 0.126 in (3.20 mm)                   | 3.0 ft-lb/in            | 160 J/m            |             |
| Thermal                                           | Typical Value (English) | Typical Value (SI) | Test Method |
| Deflection Temperature Under Load                 |                         |                    | ASTM D648   |
| 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm) | 275 °F                  | 135 °C             |             |
| Electrical                                        | Typical Value (English) | Typical Value (SI) | Test Method |
| Surface Resistivity                               | > 1.0E+12 ohms          | > 1.0E+12 ohms     | ASTM D257   |
| Flammability                                      | Typical Value (English) | Typical Value (SI) | Test Method |
| Flame Rating (0.0591 in (1.50 mm))                | V-0                     | V-0                | UL 94       |

### Processing Information

| Injection              | Typical Value (English) | Typical Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature     | 230 to 266 °F           | 110 to 130 °C      |
| Drying Time            | 4.0 to 6.0 hr           | 4.0 to 6.0 hr      |
| Processing (Melt) Temp | 536 to 590 °F           | 280 to 310 °C      |
| Mold Temperature       | 176 to 248 °F           | 80.0 to 120 °C     |

#### Injection Notes

Injection Pressure: MED-HIGH  
Hold Pressure: MED-HIGH  
Screw Speed: MODERATE  
Back Pressure: LOW

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

**Notes**<sup>1</sup> Typical values are not to be construed as specifications.<sup>2</sup> 0.20 in/min (5.0 mm/min)<sup>3</sup> 0.051 in/min (1.3 mm/min)**CONTACT INFORMATION****Americas**United States - Avon Lake  
+1 440 930 1000United States - McHenry  
+1 815 385 8500**Asia**China - Guangzhou  
+86 20 8732 7260China - Shenzhen  
+86 755 2969 2888China - Suzhou  
+86 512 6823 24 38China - Suzhou  
+86 512 6265 2600Hong Kong -  
+852 2690 5332Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849**Europe**Germany - Gaggenau  
+49 7225 6802 0Spain - Barbastro (Huesca)  
+34 974 310 314*Beyond Polymers.**Better Business Solutions.™*[www.polyone.com](http://www.polyone.com)**PolyOne Americas**33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE**PolyOne Asia**No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188**PolyOne Europe**6 Giällewee  
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.