



Edgetek™ PK-30GF/000 NC

Polyetheretherketone

Key Characteristics

Product Description	
30 % Glass Fiber Reinforced PEEK Compound with Standard Flowability	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.48	1.48	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/2.16 kg)	3.0 g/10 min	3.0 g/10 min	ISO 1133
Molding Shrinkage (0.118 in (3.00 mm))	0.20 to 0.50 %	0.20 to 0.50 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	26100 psi	180 MPa	ASTM D638
Tensile Elongation (Break)	3.0 to 4.0 %	3.0 to 4.0 %	ASTM D638
Flexural Modulus ³	1.60E+6 psi	11000 MPa	ASTM D790
Flexural Strength ³	39200 psi	270 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	2.2 ft·lb/in	120 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	608 °F	320 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	302 to 320 °F	150 to 160 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	662 to 734 °F	350 to 390 °C
Middle Temperature	662 to 734 °F	350 to 390 °C
Front Temperature	662 to 734 °F	350 to 390 °C
Mold Temperature	338 to 374 °F	170 to 190 °C

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions. SM