



## Edgetek™ SF-30GF/000 NC005

### Polyphenylene Sulfide

#### Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Natural Color
Processing Method	• Injection Molding

#### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.56	1.56	ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 8.0E-3 in/in	0.20 to 0.80 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2</sup>	20300 psi	140 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	1.5 %	1.5 %	ASTM D638
Flexural Modulus <sup>3</sup>	1.60E+6 psi	11000 MPa	ASTM D790
Flexural Strength <sup>3</sup>	30500 psi	210 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	2.0 ft·lb/in	110 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	500 °F	260 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94

#### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	284 to 302 °F	140 to 150 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	608 to 626 °F	320 to 330 °C
Middle Temperature	608 to 626 °F	320 to 330 °C
Front Temperature	608 to 626 °F	320 to 330 °C
Mold Temperature	284 to 320 °F	140 to 160 °C

#### Injection Notes

Injection Pressure: MED-HIGH  
Hold Pressure: MED-HIGH  
Screw Speed: MODERATE  
Back Pressure: LOW

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 0.20 in/min (5.0 mm/min)

<sup>3</sup> 0.051 in/min (1.3 mm/min)



*Beyond Polymers.*

*Better Business Solutions. SM*