



Elastamax™ HTE 1101

Styrene Butadiene Block Copolymer

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose		
Uses	• Automotive Interior Parts • Consumer Applications	• General Purpose • Industrial Applications	
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.00	1.00	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	800 psi	5.52 MPa	ASTM D412A
Tensile Elongation ² (Break)	550 %	550 %	ASTM D412A
Tear Strength ³	192 lbf/in	33.6 kN/m	ASTM D624
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 5 sec)	45	45	ASTM D2240

Notes

¹ Typical values are not to be construed as specifications.

² 20 in/min (510 mm/min)

³ Die C, 20 in/min (510 mm/min)