



Maxxam™ FR PP 301 NATL S

Polypropylene

Key Characteristics

Product Description

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Homopolymer	
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.980	0.980	ASTM D792
Melt Mass-Flow Rate (MFR) ² (230°C/2.16 kg)	4.0 to 12 g/10 min	4.0 to 12 g/10 min	ASTM D1238
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ³ (Yield)	4100 psi	28.3 MPa	ASTM D638
Tensile Elongation ³ (Break)	230 %	230 %	ASTM D638
Flexural Modulus	160000 psi	1100 MPa	ASTM D790
Poisson's Ratio	0.43	0.43	ASTM D638
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 in (3.18 mm), Injection Molded	0.50 ft·lb/in	27 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	194 °F	90.0 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Dielectric Strength	1000 V/mil	41 kV/mm	ASTM D149
Comparative Tracking Index (CTI)	PLC 0	PLC 0	UL 746
High Amp Arc Ignition (HAI)			UL 746
0.030 in (0.75 mm)	PLC 1	PLC 1	
0.06 in (1.5 mm)	PLC 1	PLC 1	
0.12 in (3.0 mm)	PLC 1	PLC 1	
High Voltage Arc Resistance to Ignition (HVAR)			UL 746
0.0295 in (0.750 mm)	PLC 1	PLC 1	
0.0591 in (1.50 mm)	PLC 1	PLC 1	
0.118 in (3.00 mm)	PLC 1	PLC 1	
High Voltage Arc Tracking Rate (HVTR)	PLC 0	PLC 0	UL 746
Hot-wire Ignition (HWI)			UL 746
0.030 in (0.75 mm)	PLC 4	PLC 4	
0.06 in (1.5 mm)	PLC 3	PLC 3	
0.12 in (3.0 mm)	PLC 2	PLC 2	

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.030 in (0.75 mm), (NC and Black)	V-0	V-0	
0.06 in (1.5 mm), (NC and Black)	V-0	V-0	
0.12 in (3.0 mm), (NC and Black)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in (0.75 mm)	1760 °F	960 °C	
0.06 in (1.5 mm)	1760 °F	960 °C	
0.12 in (3.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in (0.75 mm)	1760 °F	960 °C	
0.06 in (1.5 mm)	1760 °F	960 °C	
0.12 in (3.0 mm)	1430 °F	775 °C	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	100 °F	37.8 °C
Drying Time	2.0 hr	2.0 hr
Rear Temperature	360 to 390 °F	182 to 199 °C
Middle Temperature	370 to 400 °F	188 to 204 °C
Front Temperature	390 to 410 °F	199 to 210 °C
Nozzle Temperature	400 to 425 °F	204 to 218 °C
Mold Temperature	60.0 to 120 °F	15.6 to 48.9 °C

Notes

¹ Typical values are not to be construed as specifications.

² Procedure A

³ Type I, 2.0 in/min (51 mm/min)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.