

# FireCon™ CPE 30-2 RoHS BLACK

# **Chlorinated Polyethylene**

## **Key Characteristics**

#### Product Description

CPE-30-2 RoHS BLACK is a RoHS compliant heavy duty thermoplastic jacket for power and control cables. It is suitable for VW1 and tray fire rated applications. CPE-30-2 RoHS BLACK has a good balance of low temperature, oil resistance and fire retardant properties.

General				
Material Status	Commercial: Active			
Regional Availability	Asia Pacific	<ul> <li>Latin America</li> </ul>	<ul> <li>North America</li> </ul>	
Uses	<ul> <li>Cable Jacketing</li> </ul>	Wire & Cable Applications		
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>			
Forms	Pellets			

### Technical Properties 1

	•		
Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.36	1.36	ASTM D792
Appearance	Pellets/Cubes	Pellets/Cubes	ASTM D2090
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	1000 psi	6.89 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Break)	1500 psi	10.3 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	350 %	350 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 10 sec)	35	35	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-31.0 °F	-35.0 °C	ASTM D746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index (0.0750 in (1.91 mm))	32 %	32 %	ASTM D2863
Additional Information			

#### Note: Pre-drying is recommended for 4 hours at 175°-185°F.

Note: Typical processing temperatures range between 320°-390°F depending upon screw design. Contact Technical Service for recommendation for specific equipment.

NOTE: Typical Properties of Molded Slab (0.075"); Not to be Construed as Specifications.

#### **Notes**

Rev: 2013-12-12 Page: 1 of 2

<sup>&</sup>lt;sup>1</sup> Typical values are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Type IV, 20 in/min (510 mm/min)