

# FireCon™ CPE 37-11 RoHS BLACK Chlorinated Polyethylene

## **Key Characteristics**

### **Product Description**

CPE-37-11 RoHS BLACK is a heavy duty thermoplastic jacket for power and control cables. It is suitable for VW1 and tray fire rated applications. CPE-37-11 RoHS BLACK offers the highest physical properties and flexibility, great surface quality, good heat shock resistance as well as ease of processing on large cables..

| General               |                                     |                                   |                                   |  |
|-----------------------|-------------------------------------|-----------------------------------|-----------------------------------|--|
| Material Status       | Commercial: Active                  |                                   |                                   |  |
| Regional Availability | Asia Pacific                        | <ul> <li>Latin America</li> </ul> | <ul> <li>North America</li> </ul> |  |
| Uses                  | <ul> <li>Cable Jacketing</li> </ul> | Wire & Cable Applications         |                                   |  |
| RoHS Compliance       | <ul> <li>RoHS Compliant</li> </ul>  |                                   |                                   |  |
| Forms                 | Pellets                             |                                   |                                   |  |

## Technical Properties 1

| Physical                                | Typical Value (English) | Typical Value (SI) | Test Method |
|---|-------------------------|--------------------|-------------|
| Density / Specific Gravity              | 1.31                    | 1.31               | ASTM D792   |
| Appearance                              | Pellets/Cubes           | Pellets/Cubes      | ASTM D2090  |
| Mechanical                              | Typical Value (English) | Typical Value (SI) | Test Method |
| Tensile Modulus <sup>2</sup>            | 1000 psi                | 6.89 MPa           | ASTM D638   |
| Tensile Strength <sup>2</sup> (Break)   | 1800 psi                | 12.4 MPa           | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break) | 350 %                   | 350 %              | ASTM D638   |
| Hardness                                | Typical Value (English) | Typical Value (SI) | Test Method |
| Durometer Hardness (Shore D, 10 sec)    | 38                      | 38                 | ASTM D2240  |
| Thermal                                 | Typical Value (English) | Typical Value (SI) | Test Method |
| Brittleness Temperature                 | -31.0 °F                | -35.0 °C           | ASTM D746   |
| Flammability                            | Typical Value (English) | Typical Value (SI) | Test Method |
| Oxygen Index (0.0750 in (1.91 mm))      | 31 %                    | 31 %               | ASTM D2863  |
| Additional Information                  |                         |                    |             |

Note: Pre-drying is recommended for 4 hours at 175°-185°F.

Note: Typical processing temperatures range between 320°-390°F depending upon screw design. Contact Technical Service for recommendation for specific equipment.

NOTE: Typical Properties of Molded Slab (0.075"); Not to be Construed as Specifications.

#### **Notes**

Rev: 2013-12-12 Page: 1 of 2

<sup>&</sup>lt;sup>1</sup> Typical values are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Type IV, 20 in/min (510 mm/min)