

P4G4K-205

DESCRIPTION: Homopolymer

FEATURES: Clarified material. Produced without animal derived components or phthalates.

APPLICATIONS: Cast Film

PROPERTY	NOMINAL VALUE	SI UNIT	NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	12	g/10 min.			D 1238
Density	0.9	g/cm ³			D 1505
Tensile Yield Strength Yield Elongation	40 7	MPa %	5700 7	psi %	D 638
Flexural Modulus 1% Secant Tangent	1740 1810	MPa	252 262	kpsi	D 790
Deflection Temperature @ 66 psi (.455 MPa)	117	°C	243	°F	D 648
Rockwell Hardness	110		110	R	D 785
Notched Izod @ 23°C	40	J/m	0.8	ft-lb/in	D 256
Gardner Impact @ 23°C	1.4	J	12	in-lb	D 5420

May--14



REGULATORY

FDA - 21 CFR 177.1520(c) 1.1a

118 Huntsman Way, Longview, TX 75602 · Tel: 903-239-5200 · Fax: 903-234-0174

The data and information represented herein refer to typical values obtained in our laboratories by the methods or apparatuses indicated, and should be so considered. Since processing variables are a major factor in product performance, this information should serve only as a guide. Since customers' testing conditions are outside our control, the reproducibility of our data in a customer's testing facility is not guaranteed. Customer should confirm results under its testing conditions. There is no implied warranty of merchantability or fitness for a particular purpose. Establishing satisfactory performance of the product for the intended application is the customer's sole responsibility. No warranty is given concerning the existence or non-existence of any patents claiming any pertinent subject matter presented herein. The Company assumes no obligation, express or implied, or liability for use of or reliance on the information and data presented.