

P4G4Z-011

DESCRIPTION: Homopolymer

FEATURES: Good stiffness. Produced without animal derived components or phthalates.

APPLICATIONS: Injection Molding: multi purpose

PROPERTY	NOMINAL VALUE	SI UNIT		NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	12	g/10 min.				D 1238
Density	0.90	g/cm ³				D 1505
Tensile Yield Strength Yield Elongation	37 8	MPa %		5400 8	psi %	D 638
Flexural Modulus 1% Secant Tangent	1480 NA	MPa		214 NA	kpsi	D 790
Deflection Temperature @ 66 psi (.455 MPa)	96	°C		205	°F	D 648
Rockwell Hardness				110	R	D 785
Notched Izod @ 23°C	20	J/m		.4	ft-lb/in	D 256
Gardner Impact @ 23°C	2	J		20	in-lb	D 5420

May-14



Regulatory

FDA – 21 CFR 177.1520 (c) 1.1a.

UL Certified 94HB

Drug Master File listed

USP Class VI certified

Notice regarding medical applications:

This Flint Hills product meets certain requirements for use in medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that this Flint Hills product is safe, lawful and technically suitable for the intended use. Flint Hills encourages its customers to review their application with a Flint Hills technical representative to ensure that this product is not used in ways for which it was not intended or tested. Flint Hills makes no warranties (express or implied), promises or guarantees concerning the suitability of this product for use in any given medical application. Not intended for use in the manufacture of any form of implanted medical or surgical device.