

**P9M6K-041A**

- DESCRIPTION:** Specialty Impact Copolymer  
**FEATURES:** Good clarity and impact resistance.  
**APPLICATIONS:** Injection Molding: Durable goods

PROPERTY	NOMINAL VALUE	SI UNIT	NOMINAL VALUE	ENGLISH UNIT	ASTM TEST METHOD
Melt Flow Rate	35	g/10 min.			D 1238
Density	0.90	g/cm <sup>3</sup>			D 1505
Tensile Yield Strength	24	MPa	3560	psi	D 638
Yield Elongation	17	%	17	%	
Flexural Modulus 1% Secant Tangent	869	MPa	130	kpsi	D 790
Deflection Temperature @ 66 psi (.455 MPa)	78	°C	172	°F	D 648
Rockwell Hardness			62	R	D 785
Notched Izod @ 23°C	320	J/m	6	ft-lb/in	D 256
Multi-Axial @ 23°C 0°C	17.6 Ductile 22.0 Ductile	J			D 3763

Jul '13



**Regulatory**

FDA - 21 CFR 177.1520 (c) 3.1a and 3.2c

---

118 Huntsman Way, Longview, TX 75602 · Tel: 1-800-985-7303

The data and information represented herein refer to typical values obtained in our laboratories by the methods or apparatuses indicated, and should be so considered. Since processing variables are a major factor in product performance, this information should serve only as a guide. Since customers' testing conditions are outside our control, the reproducibility of our data in a customer's testing facility is not guaranteed. Customer should confirm results under its testing conditions. There is no implied warranty of merchantability or fitness for a particular purpose. Establishing satisfactory performance of the product for the intended application is the customer's sole responsibility. No warranty is given concerning the existence or non-existence of any patents claiming any pertinent subject matter presented herein. The Company assumes no obligation, express or implied, or liability for use of or reliance on the information and data presented. FHR disclaims all product warranties expressed or implied, including warranties of fitness for particular purpose or of merchantability. Further, this product is not intended for use in the manufacture of any form of implanted medical or surgical device.