



## Sheet/Thermoforming Grade Products

<b>Homopolymer</b>						
Products	Melt Flow (g/10 min)	Izod @ 23C (ft-lb/in)	Flex Modulus Tangent (kpsi)	FDA Compliance	Special Features	End-Use Application
23N2A	2.3	0.4	326	21CFR 177.1520 (c) 1.1a	High Flexural Modulus and High Heat Deflection Temperature	Thermoforming, Extrusion
<b>Random Copolymer</b>						
Products	Melt Flow (g/10 min)	Izod @ 23C (ft-lb/in)	Flex Modulus Tangent (kpsi)	FDA Compliance	Special Features	End-Use Application
23H2A	2	4.1	174	21CFR 177.1520 (c) 3.2a	Excellent Clarity	Thermoforming: Replacement for PET, PS and PC high clarity applications
23T2A	2	2.6	164	21CFR 177.1520 (c) 3.2a	Good clarity and impact strength	Thermoformed Containers
P5L2K-055	2	1	189	21CFR 177.1520 (c) 3.2a	Clarified, Best Clarity	Thermoformed Reuseable Containers & Medical Containers
<b>Speciality</b>						
Products	Melt Flow (g/10 min)	Izod @ 23C (ft-lb/in)	Flex Modulus Tangent (kpsi)	FDA Compliance	Special Features	End-Use Application
P9G1Z-047	0.55	1.7	180	21CFR 177.1520 (c) 3.2a	Fract. MFR	Thick sheet

\* Food type limited.