



Dynaflex™ G2745

Thermoplastic Elastomer

Key Characteristics

Product Description

- Dynaflex™ G2745 is designed for injection molding, however, can also be process by extrusion and injection molding.
- Easy Processing
 - Excellent Colorability
 - Excellent Ozone Resistance and Heat Aging

General

Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Features	• Good Colorability • Heat Aging Resistant • Good Processability • Ozone Resistant
Uses	• Consumer Applications • Personal Care • Overmolding • Soft Touch Applications
Agency Ratings	• BfR XXI, section 2.1.3.1.1 ¹ • FDA 21 CFR 177.1210 ²
RoHS Compliance	• RoHS Compliant
Appearance	• Clear/Transparent
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding

Technical Properties ³

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.890	0.890	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{4, 5} (300% Strain, 73°F (23°C))	400 psi	2.76 MPa	ASTM D412
Tensile Strength ^{4, 5} (Break, 73°F (23°C))	740 psi	5.10 MPa	ASTM D412
Tensile Elongation ^{4, 5} (Break, 73°F (23°C))	600 %	600 %	ASTM D412
Tear Strength ⁵ (73°F (23°C))	156 lbf/in	27.3 kN/m	ASTM D624
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	42	42	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec ⁻¹	35.0 Pa·s	35.0 Pa·s	
392°F (200°C), 11200 sec ⁻¹	9.90 Pa·s	9.90 Pa·s	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	385 to 400 °F	196 to 204 °C
Front Temperature	400 to 420 °F	204 to 216 °C
Nozzle Temperature	420 to 450 °F	216 to 232 °C
Mold Temperature	75.0 to 150 °F	23.9 to 65.6 °C
Back Pressure	0.00 to 80.0 psi	0.00 to 0.552 MPa

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection Notes

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or polyethylene (PE) carrier are most suitable for coloring Dynaflex™ G2745. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Liquid color can be used, but mineral oil based carriers may have a significant effect on the final hardness value. Concentrates based on PVC should not be used. A high color match consistency can be obtained by using precolored compounds available from GLS. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynaflex™ G2745 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynaflex™ G2745 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 0.5 to 3 in/sec
1st Stage - Boost Pressure: 400 to 900 psi

Notes

- ¹ Please contact GLS Thermoplastic Elastomers for a copy of the BfR compliance letter.
- ² Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.
- ³ Typical values are not to be construed as specifications.
- ⁴ Die C
- ⁵ 2 hr

CONTACT INFORMATION

Americas	Asia	Europe
United States - Avon Lake +1 440 930 1000	China - Guangzhou +86 20 8732 7260	Germany - Gaggenau +49 7225 6802 0
United States - McHenry +1 815 385 8500	China - Shenzhen +86 755 2969 2888	Spain - Barbaastro (Huesca) +34 974 310 314
	China - Suzhou +86 512 6823 24 38	
	China - Suzhou +86 512 6265 2600	
	Hong Kong - +852 2690 5332	
	Taiwan - Yonghe City, +886 9396 99740, +886 2929 1849	



Beyond Polymers.
Better Business Solutions. SM
www.polyone.com

PolyOne Americas 33587 Walker Road Avon Lake, Ohio 44012 United States +1 440 930 1000 +1 866 POLYONE	PolyOne Asia No. 88 Guoshoujing Road Z.J Hi-tech Park, Pudong Shanghai, 201203, China +86 21 5080 1188	PolyOne Europe 6 Giällewee +352 269 050 35
---	---	---

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.