



Nymax™ GF 1200 A 33 HS Natural Polyamide 66

Key Characteristics

Product Description

The Nymax® GF 1200 Series of glass fiber-reinforced nylon 6/6 compounds have been specifically formulated for applications requiring high stiffness, tensile properties, heat resistance, and durability in harsh environments. These materials are available in a broad range of reinforcement levels depending upon stiffness characteristics desired and have been formulated to offer ease of processing in most standard thermoplastic processing equipment

General

Material Status	• Commercial: Active		
Regional Availability	• North America	• South America	
Filler / Reinforcement	• Glass Fiber Reinforcement, 33% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• General Purpose	• Heat Stabilized	
Uses	• Automotive Applications	• Consumer Applications	• Industrial Applications
	• Construction Applications	• General Purpose	
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.38	1.38	ASTM D792
Molding Shrinkage - Flow	0.30 in/in	30 %	ASTM D955
Water Absorption (24 hr, 0.125 in (3.18 mm))	1.0 %	1.0 %	ASTM D570
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	28500 psi	197 MPa	ASTM D638
Tensile Elongation ² (Break)	3.8 %	3.8 %	ASTM D638
Flexural Modulus	1.30E+6 psi	8960 MPa	ASTM D790
Flexural Strength	40000 psi	276 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	2.40 ft-lb/in	128 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	482 °F	250 °C	
Melting Temperature	500 °F	260 °C	
Additional Properties			
Molded Test Bars: Dry as Molded			

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

CONTACT INFORMATION

Americas

Argentina - Buenos Aires
+0054 11 4200 5917

Brasil - Campinas
+55 19 3206 0561

Mexico - Toluca
+52 722 2790200

United States - Avon Lake
+1 440 930 1000

Asia

China - Shenzhen
+86 (0) 755 2969 2888

China - Suzhou
+86 (0) 512 6823 24 38

India - Mumbai
+91 9820 194 220

Singapore - Singapore
+65 (0) 6861 9325

Europe

Germany - Gaggenau
+49 (0) 7225 6802 0

Spain - Barbastro (Huesca)
+34 (0) 9 7431 0314

Turkey - Cekmece-Istanbul-Türkiye
+90 (0) 212 549 2256

United Kingdom - Widnes
+44 (0) 05600 760 800



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 (0) 21 5080 1188

PolyOne Europe

2 Rue Melville Wilson
5330 Assesse, Belgium
+32 (0) 83 660 211