

GLS POLYMERS PVT.LTD

(Manufacturer of Blends, compounds & Reactive polymers)



Product Data Sheet

Product :- ABS 30 GF Precolor

Grade :- SG69

	UNIT	VALUE	ASTM
Specific Gravity	-----	1.21 -1.25	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	g/10 min	8 min	D 1238
Molding Shrinkage 3.2 mmsection	%	0.1 - 0.3	D 955
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	J/m	40 Min	D 256
Tensile Strength @ yield 50mm/min	MPa	72 Min	D 638
Tensile Modulus	MPa	6600 Min	D 638
Flexural Strength	MPa	87 Mim	D 790
Flexural Modulus	MPa	4800 min	D 790
THERMAL			
Heat Deflection Temperature			
@ 264 psi (1820 kPa)	°C	102 Min	D 648
@ 66 psi (455 kPa)	°C	105Min	D 648
Flammability**	-----	HB	UL94
GENERAL PROCESSING FOR INJECTION MOLDING			
Injection Pressure	MPa	69-102	
Melt Temperature	°C	205-235	
Mold Temperature	°C	60-85	
Drying	hr @ °C	2@ 80	
Data herein is typical and not to be construed as specifications. Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties. The Above mentioned tchnical data is purely indicative and is given without any guarantee			
GLS POLYMERS PVT LTD, #415, 11th CROSS, 4th PHASE, PIA, BANGALORE-560 058, INDIA glsp@glspolymers.com			