

GLS POLYMERS PVT.LTD
(Manufacturer of Blends, compounds & Reactive polymers)



Product Data Sheet
Product : PP FR V2 Precolor
Grade : YN08

	UNIT	VALUE	ASTM
Specific Gravity	-----	0.94-0.96	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	g/10 min	Min 5	D 1238
Molding Shrinkage 3.2 mm section	%	1.5 - 2.0	D 955
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	J/m	80 - 120	D 256
Tensile Strength	MPa	23 - 27	D 638
Tensile Elongation @ Yield	%	> 10	D 638
Flexural Strength	MPa	28 -34	D 790
Flexural Modulus	MPa	1200 -1300	D 790
THERMAL			
Heat Deflection Temperature			
@ 264 psi (1820 kPa)	°C	53 -55	D 648
Flammability**	-----	V2	UL94
GENERAL PROCESSING FOR INJECTION MOLDING			
Injection Pressure	MPa	65 -105	
Melt Temperature	°C	190 - 230	
Mold Temperature	°C	32-64	
Drying	hr @ °C	2 @ 78	
<p>Data herein is typical and not to be construed as specifications. Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties. The Above mentioned tchnical data is purely indicative and is given without any guarantee . Values as GLS Polymers tested</p>			
<p align="center">GLS POLYMERS PVT LTD, #415, 11th CROSS, 4th PHASE, PIA, BANGALORE-560 058, INDIA Visit us at - www.glspolymers.com Contact : glsp@glspolymers.com</p>			

