

GLS POLYMERS PVT.LTD

(Manufacturer of Blends, compounds & Reactive Polymers)



Product Data Sheet

Product : PP 20 TALC

Grade : YT49

	UNIT	VALUE	ASTM
Specific Gravity	-----	1.05 - 1.06	D 792
Melt Flow Rate @ 230 °C / 2.16 kg	g/10 min	6 - 10	D 1238
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	J/m	55 - 70	D 256
Tensile Strength	MPa	23 - 27	D 638
Tensile Elongation @ Yield	%	> 5	D 638
Flexural Strength	MPa	25 - 30	D 790
Flexural Modulus	MPa	1800 - 2000	D 790
THERMAL			
Heat Deflection Temperature			
@ 264 psi (1820 kPa)	°C	75 - 80	D 648
GENERAL PROCESSING FOR INJECTION MOLDING			
Injection Pressure	MPa	65 -105	
Melt Temperature	°C	190 - 220	
Mold Temperature	°C	32-64	
Drying	hr @ °C	2 @ 78	
Data herein is typical and not to be construed as specifications. Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties. The Above mentioned technical data is purely indicative and is given without any guarantee . Values as GLS Polymers tested.			
GLS POLYMERS PVT LTD,#415,11th CROSS,4th PHASE, PIA, BANGALORE-560 058, INDIA			