

Dynalloy™ GP 7810-60T

热塑性弹性体

关键特性

产品说明

Dynalloy™ GP 7810-60T 是一款主要为消费品市场开发的热塑性弹性体，例如厨房用具，玩具，个人和婴幼儿护理用品等等。该系列是由氢化的苯乙烯嵌段共聚物为基材改性而成。

总览

材料状态	• 已商用：当前有效
供货地区	• 亚太地区
机构评级	• FDA 21 CFR 177.1210 ¹ • FDA 21 CFR 177.2600 ¹ • 欧洲 10/1/2011 12:00:00 AM ²
RoHS 合规性	• RoHS 合规
外观	• 半透明
形式	• 粒子
加工方法	• 注射成型

技术特性³

物理性能	典型值 (英语)	典型值 (公尺)	测试方法
密度 / 比重	0.870	0.870	ASTM D792
弹性体	典型值 (英语)	典型值 (公尺)	测试方法
拉伸应力 ^{4,5} (300%应变, 73°F (23°C))	380 psi	2.62 MPa	ASTM D412
抗张强度 ^{4,5} (屈服, 73°F (23°C))	1010 psi	6.96 MPa	ASTM D412
伸长率 ^{4,5} (断裂, 73°F (23°C))	760 %	760 %	ASTM D412
撕裂强度	177 lbf/in	31.0 kN/m	ASTM D624
压缩永久变形 (73°F (23°C), 22 hr)	13 %	13 %	ASTM D395
硬度	典型值 (英语)	典型值 (公尺)	测试方法
邵氏硬度 (邵氏 A, 10 秒)	60	60	ASTM D2240
充模分析	典型值 (英语)	典型值 (公尺)	测试方法
表观粘度 (392°F (200°C), 11200 sec ⁻¹)	6.60 Pa·s	6.60 Pa·s	ASTM D3835

加工信息

注射	典型值 (英语)	典型值 (公尺)
建议的最大回料比例	20 %	20 %
料筒后部温度	331 到 370 °F	166 到 188 °C
料筒中部温度	351 到 379 °F	177 到 193 °C
料筒前部温度	370 到 441 °F	188 到 227 °C
射嘴温度	360 到 421 °F	182 到 216 °C
加工 (熔体) 温度	379 到 441 °F	193 到 227 °C
模具温度	60 到 100 °F	16 到 38 °C

© 2021 普立万公司版权所有。普立万公司对于该文件中内容的准确性、适用性或者使用该文件的内容后产生的后果不做任何保证。该文件中的某些信息来自运用小型设备的实验室检测，这些信息可能无法可靠指明使用大型设备时得到的性能或者指标。“典型”数值或者没有给出范围的数值不能表明最小或者最大性能；对于性能范围和最大/最小规格方面的信息，请咨询您的销售代表。加工条件可能会导致材料性质背离该文件中给出的数值。普立万公司对于该产品或者用于您工艺或者终端应用的信息的适用性不做出任何保证。您有责任进行全面的终端产品性能测试，以便确定该公司的产品是否适用于您的应用工艺中，同时您要考虑到您使用本文件以及使用该产品可能导致的所有风险和责任。未经专利拥有者的许可，该数据表不得被视为允许、建议或者暗示使用任何专利发明成果。

注射说明

Color concentrates with polypropylene (PP), ethylene vinyl acetate (EVA), or low density polyethylene (PE) carriers are most suitable for coloring Dynalloy™ GP 7810. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow from 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials. Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP). Regrind levels up to 20% can be used with Dynalloy™ GP 7810 with minimal property losses, provided that the regrind is free of contamination.

To minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind effectiveness should be determined by the customer.

The Dynalloy™ GP 7810 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

备注

¹ Contact GLS Thermoplastic Elastomers for a copy of the FDA Compliance letter

² Contact GLS Thermoplastic Elastomers for a copy of the EU Compliance letter

³ 典型值不用于解释规格书

⁴ C 模具

⁵ 2 小时