



Geon™ Vinyl Cellular E2501

Rigid Polyvinyl Chloride

Key Characteristics

Product Description

Geon E2501 is an interior grade of standard E2500.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Automotive Interior Parts	• Building Materials	
Forms	• Cellular, Inward Foam	• Powder	
Processing Method	• Extrusion		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity ²	0.600 to 0.800	0.600 to 0.800	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ³	490000 psi	3380 MPa	ASTM D638
Tensile Strength ³ (Yield)	7480 psi	51.6 MPa	ASTM D638
Flexural Modulus	496000 psi	3420 MPa	ASTM D790
Flexural Strength	14000 psi	96.8 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact - Across Flow 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	0.70 ft-lb/in	37 J/m	ASTM D256A
Drop Impact Resistance ⁴ (73°F (23°C))	0.230 in-lb/mil	10.2 J/cm	ASTM D4226
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	85	85	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	158 °F	70.0 °C	ASTM D648
CLTE - Flow	3.3E-5 in/in/°F	5.9E-5 cm/cm/°C	ASTM D696
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (natural)	V-0	V-0	UL 94

Additional Information

Physical properties measured on non-foamed profiles.

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	360 to 375 °F	182 to 191 °C

Notes

¹ Typical values are not to be construed as specifications.

² Cellular

³ Type I, 0.20 in/min (5.1 mm/min)

⁴ Procedure A, C.125 Dart