



Geon™ Vinyl Flexible 90252

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose		
Uses	• Automotive Applications • Gaskets	• General Purpose • Protective Coverings	• Seals
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.30	1.30	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (100% Strain)	1150 psi	7.90 MPa	ASTM D638
Tensile Strength ² (Break)	2410 psi	16.6 MPa	ASTM D638
Tensile Elongation ² (Break)	400 %	400 %	ASTM D638
Tear Resistance ³	370 lbf/in	64.0 kN/m	ASTM D1004
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A	88	88	
Shore A, 15 sec	80	80	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-25.6 °F	-32.0 °C	ASTM D746

Notes

¹ Typical values are not to be construed as specifications.

² Type IV, 20 in/min (510 mm/min)

³ Die C, 2 in/min