



Geon™ Vinyl Flexible A7501

Flexible Polyvinyl Chloride

Key Characteristics

Product Description			
Interior applications.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• High Gloss	
Uses	• General Purpose		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.18	1.18	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (100% Strain)	850 psi	5.86 MPa	ASTM D638
Tensile Strength ² (Break)	2000 psi	13.8 MPa	ASTM D638
Tensile Elongation ² (Break)	400 %	400 %	ASTM D638
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength ³	250 lbf/in	43.8 kN/m	ASTM D624
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A	75	75	
Shore A, 15 sec	68	68	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-47.0 °F	-43.9 °C	ASTM D746

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	380 to 400 °F	193 to 204 °C
Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	345 to 355 °F	174 to 179 °C

Notes

¹ Typical values are not to be construed as specifications.

² 20 in/min (510 mm/min)

³ Die C, 20 in/min (510 mm/min)