



Geon™ Vinyl Flexible C8500

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• Medium Gloss	
Uses	• General Purpose		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.42	1.42	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (100% Strain)	1050 psi	7.24 MPa	ASTM D638
Tensile Strength ² (Break)	1900 psi	13.1 MPa	ASTM D638
Tensile Elongation ² (Break)	360 %	360 %	ASTM D638
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength ³	320 lbf/in	56.0 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	22 %	22 %	ASTM D395
Clash-Berg Modulus			ASTM D1043
--	49400 psi	341 MPa	
-29°F (-34°C)	45000 psi	310 MPa	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			ASTM D2240
Shore A	85	85	
Shore A, 15 sec	78	78	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-24.0 °F	-31.1 °C	ASTM D746

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	380 to 400 °F	193 to 204 °C
Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	345 to 355 °F	174 to 179 °C

Notes

¹ Typical values are not to be construed as specifications.

² 20 in/min (510 mm/min)

³ Die C, 20 in/min (510 mm/min)