



Geon™ Vinyl Flexible D6500

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• Low Gloss	
Uses	• General Purpose		
Forms	• Pellets		
Processing Method	• Extrusion		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.49	1.49	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (100% Strain)	500 psi	3.45 MPa	ASTM D638
Tensile Strength ² (Break)	1000 psi	6.89 MPa	ASTM D638
Tensile Elongation ² (Break)	360 %	360 %	ASTM D638
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength ³	130 lbf/in	22.8 kN/m	ASTM D624
Compression Set (73°F (23°C), 22 hr)	30 %	30 %	ASTM D395
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 15 sec)	61	61	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-34.0 °F	-36.7 °C	ASTM D746

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	335 to 345 °F	168 to 174 °C

Notes

¹ Typical values are not to be construed as specifications.

² 20 in/min (510 mm/min)

³ Die C, 20 in/min (510 mm/min)