

# Geon™ Vinyl Flexible HC18080G Flexible Polyvinyl Chloride

### **Key Characteristics**

General		
Material Status	Commercial: Active	
Regional Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li><li>North America</li></ul>
Features	Food Contact Acceptable	Radiation (Gamma)     Resistant
Uses	<ul> <li>Medical Devices</li> </ul>	
Agency Ratings	<ul> <li>FDA Food Contact, Unspecified Rating</li> </ul>	FDA Unspecified Rating
Appearance	<ul> <li>Clear/Transparent</li> </ul>	
Forms	• Pellets	
Processing Method	<ul> <li>Extrusion</li> </ul>	Injection Molding

## Technical Properties 1

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.23	1.23	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2</sup> (100% Strain)	1600 psi	11.0 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Break)	2550 psi	17.6 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	340 %	340 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	80	80	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-32.8 °F	-36.0 °C	ASTM D746

#### Additional Information

NOTE: All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is "For foods of high water content only". This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application.

#### Notes

<sup>1</sup> Typical values are not to be construed as specifications.

Rev: 2016-01-26 Page: 1 of 2

<sup>&</sup>lt;sup>2</sup> Type IV, 20 in/min (510 mm/min)