



Geon™ Vinyl Flexible MD403KB

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• Flame Retardant	• Low Gloss	• UV Absorbing
Uses	• Electrical/Electronic Applications	• Profiles	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	• Profile Extrusion

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.48	1.48	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	1950 psi	13.4 MPa	ASTM D638
Tensile Elongation ² (Break)	310 %	310 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 15 sec)	83	83	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-13.0 °F	-25.0 °C	ASTM D746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index (0.125 in (3.18 mm))	32 %	32 %	ASTM D2863

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	380 to 400 °F	193 to 204 °C
Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	350 to 360 °F	177 to 182 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type IV, 20 in/min (510 mm/min)