



Geon™ Vinyl Flexible MG26

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose		
Uses	• Automotive Bumper • General Purpose	• Hose • Tubing	
Forms	• Pellets		
Processing Method	• Extrusion	• Profile Extrusion	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.45	1.45	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	2080 psi	14.3 MPa	ASTM D638
Tensile Elongation ² (Break)	250 %	250 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 15 sec)	80	80	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-13.0 °F	-25.0 °C	ASTM D746

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	355 to 365 °F	179 to 185 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type IV, 20 in/min (510 mm/min)