



Geon™ Vinyl Flexible R290AE

Flexible Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• UV Stabilizer		
Features	• High Gloss	• UV Absorbing	
Uses	• Profiles		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	• Profile Extrusion

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.30	1.30	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ² (Break)	3450 psi	23.8 MPa	ASTM D638
Tensile Elongation ² (Break)	200 %	200 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 15 sec)	62	62	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	27.0 °F	-2.78 °C	ASTM D746
Additional Information			

Durometer Hardness, ASTM D2240, D Scale (15 sec): 60 to 64

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	380 to 410 °F	193 to 210 °C
Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	355 to 375 °F	179 to 191 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type IV, 20 in/min (510 mm/min)