

## Geon™ Vinyl Flexible XV3906 Flexible Polyvinyl Chloride

## **Key Characteristics**

| eneral                |   |  |                    |
|-----------------------|---|--|--------------------|
| Material Status       | Commercial: Active  |  |                    |
| Regional Availability | <ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul>               | North America      |
| Features              | <ul> <li>Food Contact Acceptable</li> </ul>                       | Non-Phthalate Plasticize                                     | er                 |
| Uses                  | <ul> <li>Medical Devices</li> </ul>                               |  |                    |
| Agency Ratings        | CPSIA Compliant   | <ul> <li>FDA Food Contact,<br/>Unspecified Rating</li> </ul> | • ISO 10993 Part 5 |
| Appearance            | <ul> <li>Clear/Transparent</li> </ul>                             |  |                    |
| Forms                 | • Pellets   |  |                    |
| Processing Method     | <ul> <li>Extrusion</li> </ul>                                     | Injection Molding  |                    |
|                       |   |  |                    |

## Technical Properties 1

|   | - ·                     |                    |             |
|---|-------------------------|--------------------|-------------|
| Physical                                    | Typical Value (English) | Typical Value (SI) | Test Method |
| Density / Specific Gravity                  | 1.21                    | 1.21               | ASTM D792   |
| Mechanical                                  | Typical Value (English) | Typical Value (SI) | Test Method |
| Tensile Strength <sup>2</sup> (100% Strain) | 1200 psi                | 8.27 MPa           | ASTM D638   |
| Tensile Strength <sup>2</sup> (Break)       | 2500 psi                | 17.2 MPa           | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break)     | 350 %                   | 350 %              | ASTM D638   |
| Hardness                                    | Typical Value (English) | Typical Value (SI) | Test Method |
| Durometer Hardness (Shore A, 15 sec)        | 75                      | 75                 | ASTM D2240  |
| Thermal                                     | Typical Value (English) | Typical Value (SI) | Test Method |
| Brittleness Temperature                     | -31.0 °F                | -35.0 °C           | ASTM D746   |
| Additional Information                      |                         |                    |             |

NOTE: All ingredients used in the formulation of this compound are listed in the United States FDA Code of Federal Regulations, Title 21. The only restriction is that the plasticizer is "For foods of high water content only". This statement is only an overview of the FDA listings for this product. It is the customer's responsibility to ensure that the compound is suitable for its intended application.

This compound has obtained conformance to Cytotoxicity tests under ISO 10993-5 GUIDELINES, when combined with Trans 1756 pigmentation.

## Notes

Rev: 2013-12-12 Page: 1 of 2

<sup>&</sup>lt;sup>1</sup> Typical values are not to be construed as specifications.

<sup>&</sup>lt;sup>2</sup> Type IV, 20 in/min (510 mm/min)