



Geon™ Vinyl Rigid Extrusion 87358

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Gloss		
Forms	• Pellets		
Processing Method	• Sheet Extrusion	• Thermoforming	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.35	1.35	ASTM D792
PVC Cell Classification	15343	15343	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	372000 psi	2560 MPa	ASTM D638
Tensile Strength ² (Yield)	6740 psi	46.5 MPa	ASTM D638
Flexural Modulus	397000 psi	2740 MPa	ASTM D790
Flexural Strength	11400 psi	78.6 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	11 ft·lb/in	580 J/m	
Across Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	6.2 ft·lb/in	330 J/m	
Flow : 73°F (23°C), 0.125 in (3.18 mm), Compression Molded	7.8 ft·lb/in	420 J/m	
Drop Impact Resistance			ASTM D4226
73°F (23°C) ³	1.42 in·lb/mil	63.2 J/cm	
73°F (23°C) ⁴	4.47 in·lb/mil	199 J/cm	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 15 sec)	81	81	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	141 °F	60.6 °C	
CLTE - Flow	4.1E-5 in/in/°F	7.4E-5 cm/cm/°C	ASTM D696

Additional Information

Note: The Cell Classification was determined using the notched Izod test with injection molded samples.

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	370 to 380 °F	188 to 193 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ Procedure A, C.125 Dart

⁴ Procedure B, C.125 Dart



Beyond Polymers.

Better Business Solutions.SM