



Geon™ Vinyl Rigid Extrusion L1361

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant		
Uses	• Piping		
Agency Ratings	• NSF STD-51	• NSF Type I	
Forms	• Pellets		
Processing Method	• Extrusion		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.38	1.38	ASTM D792
PVC Cell Classification	12454	12454	ASTM D1784
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	410000 psi	2830 MPa	ASTM D638
Tensile Strength ² (Yield)	7330 psi	50.5 MPa	ASTM D638
Flexural Modulus	420000 psi	2900 MPa	ASTM D790
Flexural Strength	15100 psi	104 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
-40°F (-40°C), 0.125 in (3.18 mm), Compression Molded	0.95 ft·lb/in	51 J/m	
Drop Impact Resistance			ASTM D4226
73°F (23°C) ³	1.40 in·lb/mil	62.3 J/cm	
73°F (23°C) ⁴	3.00 in·lb/mil	133 J/cm	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 15 sec)	81	81	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	158 °F	70.0 °C	
CLTE - Flow	2.9E-5 in/in/°F	5.2E-5 cm/cm/°C	ASTM D696
Additional Information	Typical Value (English)	Typical Value (SI)	
Ease of Sizing	Good	Good	

Processing Information

Extrusion	Typical Value (English)	Typical Value (SI)
Melt Temperature	360 to 380 °F	182 to 193 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ Procedure A, C.125 Dart

⁴ Procedure B, C.125 Dart



Beyond Polymers.

Better Business Solutions.SM