



Geon™ Vinyl Rigid Molding M3530

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Impact Resistance	• Medium Flow	
Uses	• Engineered Applications		
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.33	1.33	ASTM D792
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3 in/in	0.20 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	329000 psi	2270 MPa	ASTM D638
Tensile Strength ² (Yield)	5700 psi	39.3 MPa	ASTM D638
Tensile Elongation ² (Break)	110 %	110 %	ASTM D638
Flexural Modulus	351000 psi	2420 MPa	ASTM D790
Flexural Strength	9790 psi	67.5 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
32°F (0°C), 0.125 in (3.18 mm), Injection Molded	19 ft·lb/in	1000 J/m	
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	23 ft·lb/in	1200 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	80	80	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.125 in (3.18 mm)	153 °F	67.0 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.125 in (3.18 mm)	136 °F	57.9 °C	ASTM D648
RTI Elec	122 °F	50.0 °C	UL 746
RTI Imp	122 °F	50.0 °C	UL 746
RTI Str	122 °F	50.0 °C	UL 746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm), ALL	V-0	V-0	
0.08 in (2.0 mm), ALL	5VA	5VA	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	390 to 410 °F	199 to 210 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)



Beyond Polymers.

Better Business Solutions. SM