



Geon™ Vinyl Rigid Molding M3800

Rigid Polyvinyl Chloride

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• High Flow	• High Impact Resistance
Uses	• Appliances • Business Equipment	• Construction Applications • Electrical/Electronic Applications	• General Purpose • Telecommunications
Agency Ratings	• NSF STD-51	• NSF STD-61	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.33	1.33	ASTM D792
Spiral Flow	44.0 in	112 cm	
Molding Shrinkage - Flow	2.0E-3 to 5.0E-3 in/in	0.20 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	330000 psi	2280 MPa	ASTM D638
Tensile Strength ² (Yield)	6000 psi	41.4 MPa	ASTM D638
Tensile Elongation ² (Break)	35 %	35 %	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Flexural Strength	9700 psi	66.9 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
0°F (-18°C), 0.125 in (3.18 mm), Injection Molded	2.0 ft·lb/in	110 J/m	
32°F (0°C), 0.125 in (3.18 mm), Injection Molded	5.0 ft·lb/in	270 J/m	
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	12 ft·lb/in	640 J/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D)	79	79	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	162 °F	72.2 °C	ASTM D648
Deflection Temperature Under Load 66 psi (0.45 MPa), Annealed, 0.250 in (6.35 mm)	167 °F	75.0 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	156 °F	68.9 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Annealed, 0.250 in (6.35 mm)	163 °F	72.8 °C	ASTM D648

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
RTI Elec	194 °F	90.0 °C	UL 746
RTI Imp	185 °F	85.0 °C	UL 746
RTI Str	194 °F	90.0 °C	UL 746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.030 in (0.75 mm), ALL	V-0	V-0	
0.06 in (1.5 mm), ALL	5VA	5VA	
Additional Information	Typical Value (English)	Typical Value (SI)	
CSA Flammability ³ (63.0 mil (1.60 mm))	• V-0 • 5VA	• V-0 • 5VA	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Processing (Melt) Temp	390 to 410 °F	199 to 210 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 2.0 in/min (51 mm/min)

³ All Colors



Beyond Polymers.

Better Business Solutions.™