



# Gravi-Tech™ GRV-NJ-110-W

## Polyamide 12

### Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• High Density • Non-Toxic		
Uses	• Industrial Applications • Medical/Healthcare Applications	• Projectiles • Radiation Shielding	• Sporting Goods • Weighting & Balancing
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	11.0	11.0	ASTM D792
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3 in/in	0.50 to 0.70 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	1.30E+6 psi	8960 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	6500 psi	44.8 MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	1.0 %	1.0 %	ASTM D638
Flexural Modulus	1.20E+6 psi	8270 MPa	ASTM D790
Flexural Strength	10000 psi	68.9 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.250 in (6.35 mm), Injection Molded	1.5 ft·lb/in	80 J/m	ASTM D256A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	311 °F	155 °C	ASTM D648

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	175 °F	79 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	500 to 550 °F	260 to 288 °C
Mold Temperature	180 to 300 °F	82 to 149 °C

### Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Type I, 0.20 in/min (5.1 mm/min)