



Gravi-Tech™ GRV-UR-110-W

Polyurethane

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific		
Features	• High Density	• Non-Toxic	
Uses	• Industrial Applications • Medical/Healthcare Applications	• Projectiles • Radiation Shielding	• Sporting Goods • Weighting & Balancing
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	11.0	11.0	ASTM D792
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	40000 psi	276 MPa	ASTM D638
Tensile Strength ² (Yield)	380 psi	2.62 MPa	ASTM D638
Tensile Elongation ² (Break)	10 %	10 %	ASTM D638
Flexural Modulus	25000 psi	172 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.250 in (6.35 mm), Injection Molded	3.0 ft·lb/in	160 J/m	ASTM D256A

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	150 °F	66 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	360 to 400 °F	182 to 204 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)