



OnForce™ LFT PP-50LGF/001 Natural

Polypropylene Homopolymer

Key Characteristics

Product Description

PolyOne's Long Fiber Thermoplastic (LFT) compounds are formulated for demanding applications which require high stiffness and good impact such as metal replacement or other structural applications. These products exhibit enhanced physical and mechanical properties versus standard short fiber products. Benefits of LFT compounds include improved impact strength, elastic modulus, and material strength across wide temperature ranges from subambient to highly elevated. Furthermore, LFT compounds have been shown to offer improved performance in the areas of creep and fatigue performance, improved dimensional stability, and exhibit an exceptional surface finish when compared to traditional highly filled short fiber products.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Long Glass Fiber, 50% Filler by Weight		
Features	• Heat Stabilized		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.30 g/cm ³	1.30 g/cm ³	ISO 1183
Molding Shrinkage			
-- ²	0.30 %	0.30 %	ISO 294-4
--	0.10 to 0.40 %	0.10 to 0.40 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus			
--	1.74E+6 psi	12000 MPa	ISO 527-2
-- ³	1.61E+6 psi	11100 MPa	ASTM D638
Tensile Stress			
Break	18900 psi	130 MPa	ISO 527-2
Break ³	16000 psi	110 MPa	ASTM D638
Tensile Strain			
Break	2.0 %	2.0 %	ISO 527-2
Break ³	1.7 %	1.7 %	ASTM D638
Flexural Modulus			
--	1.31E+6 psi	9000 MPa	ISO 178
-- ⁴	1.37E+6 psi	9470 MPa	ASTM D790
Flexural Stress			
--	26100 psi	180 MPa	ISO 178
-- ⁴	27200 psi	188 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	12 ft·lb/in ²	25 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	29 ft·lb/in ²	60 kJ/m ²	ISO 179
Notched Izod Impact	3.2 ft·lb/in	170 J/m	ASTM D256
Unnotched Izod Impact	16 ft·lb/in	830 J/m	ASTM D256
Gardner Impact	105 in·lb	11.9 J	ASTM D5420

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	325 °F	163 °C	
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	306 °F	152 °C	
Heat Deflection Temperature			ISO 75-2/C
1160 psi (8.0 MPa), Unannealed	291 °F	144 °C	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80.0 °C
Drying Time	2.0 hr	2.0 hr
Processing (Melt) Temp	410 to 446 °F	210 to 230 °C
Mold Temperature	140 °F	60.0 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	145 psi	1.00 MPa

Injection Notes

LFT compounds can be processed using equipment similar to that used for short fiber products. The mechanical properties of finished parts depend greatly on the length of the fibers in the molded part; therefore processing conditions must be set carefully in order to minimize fiber breakage. A "low shear process" is advised, with low back pressure, low screw speed and low-to-medium injection speed.

Notes

¹ Typical values are not to be construed as specifications.

² Measured on a tensile specimen. Actual mold shrinkage values are highly dependant on part geometry, mold configuration, and processing conditions.

³ 0.20 in/min (5 mm/min)

⁴ 0.050 in/min (1.3 mm/min)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.