



LubriOne™ AS-000/15T

Acrylonitrile Butadiene Styrene

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	
Features	• Lubricated		
Uses	• Appliance Components	• Conveyor Parts	• Printer Parts
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.16	1.16	ASTM D792
Molding Shrinkage - Flow	3.0E-3 to 4.0E-3 in/in	0.30 to 0.40 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	200000 psi	1380 MPa	ASTM D638
Tensile Strength ² (Break)	5000 psi	34.5 MPa	ASTM D638
Tensile Elongation ² (Break)	13 %	13 %	ASTM D638
Flexural Modulus	200000 psi	1380 MPa	ASTM D790
Flexural Strength	11500 psi	79.3 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.250 in (6.35 mm), Injection Molded	1.4 ft-lb/in	76 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Annealed, 0.125 in (3.18 mm)	203 °F	95.0 °C	
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Annealed, 0.125 in (3.18 mm)	185 °F	85.0 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 185 °F	80 to 85 °C
Drying Time	2.0 hr	2.0 hr
Mold Temperature	149 to 185 °F	65 to 85 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)
