



LubriOne™ AT-000/10T 2S NATURAL

Acetal (POM) Copolymer

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Copolymer • Low Friction	• Lubricated • Wear Resistant	
Uses	• Appliance Components • Automotive Applications • Bearings • Business Equipment	• Consumer Applications • Conveyor Parts • Gears • Industrial Applications	• Printer Parts • Pulleys • Rollers
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.46	1.46	ASTM D792
Molding Shrinkage - Flow	0.020 to 0.030 in/in	2.0 to 3.0 %	ASTM D955
Molding Shrinkage - Across Flow	0.010 to 0.030 in/in	1.0 to 3.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	389000 psi	2680 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield ³	6700 psi	46.2 MPa	
Yield ²	6100 psi	42.1 MPa	
Tensile Strength ² (Break)	6100 psi	42.1 MPa	ASTM D638
Tensile Elongation ² (Break)	42 %	42 %	ASTM D638
Flexural Modulus ⁴	273000 psi	1880 MPa	ASTM D790
Flexural Strength ⁴	9800 psi	67.6 MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.11	0.11	
vs. Steel - Static	0.14	0.14	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.125 in (3.18 mm), Injection Molded	0.90 ft·lb/in	48 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed, 0.250 in (6.35 mm)	302 °F	150 °C	

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.250 in (6.35 mm)	180 °F	82.2 °C	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	200 °F	93 °C
Drying Time	1.0 to 2.0 hr	1.0 to 2.0 hr
Suggested Max Moisture	0.15 to 0.20 %	0.15 to 0.20 %
Rear Temperature	330 to 350 °F	166 to 177 °C
Middle Temperature	350 to 370 °F	177 to 188 °C
Front Temperature	370 to 390 °F	188 to 199 °C
Nozzle Temperature	380 to 410 °F	193 to 210 °C
Mold Temperature	170 to 200 °F	77 to 93 °C

Notes

¹ Typical values are not to be construed as specifications.

² Type I, 0.20 in/min (5.1 mm/min)

³ Type I, 2.0 in/min (51 mm/min)

⁴ 0.050 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions. SM