



LubriOne™ ATC-000/15T Black

Acetal (POM) Copolymer

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Heat Stabilized • UV Stabilized • Lubricated • Wear Resistant
Uses	• Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.46 to 1.50 g/cm ³	1.46 to 1.50 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	348000 psi	2400 MPa	ISO 527-2
Tensile Stress	6960 psi	48.0 MPa	ISO 527-2
Tensile Strain (Break)	10 %	10 %	ISO 527-2
Flexural Modulus	290000 psi	2000 MPa	ISO 178
Flexural Stress	9430 psi	65.0 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.9 ft·lb/in ²	4.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	19 ft·lb/in ²	40 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	284 °F	140 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	176 °F	80.0 °C	ISO 75-2/A
Vicat Softening Temperature	302 °F	150 °C	ISO 306
Melting Temperature (DSC)	329 to 338 °F	165 to 170 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.12 in (3.0 mm))	HB	HB	UL 94
FMVSS Burning Speed	< 4 in/min	< 100 mm/min	DIN 75200

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 212 °F	80 to 100 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	356 to 410 °F	180 to 210 °C

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	140 to 212 °F	60 to 100 °C

Notes

¹ Typical values are not to be construed as specifications.



Beyond Polymers.

Better Business Solutions. SM