



LubriOne™ NY-25M/02M schwarz HI SO

Polyamide 6

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Low Friction • Lubricated • Wear Resistant
Uses	• Appliance Components • Consumer Applications • Printer Parts • Automotive Applications • Conveyor Parts • Pulleys • Bearings • Gears • Rollers • Business Equipment • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ² (73°F (23°C))	1.32 g/cm ³	1.32 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	450000 psi	3100 MPa	ISO 527-2/1
Tensile Stress Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	8990 psi	62.0 MPa	ISO 527-2/5
Tensile Strain Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	> 6.0 %	> 6.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength 73°F (23°C), Injection Molded	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 179
Unnotched Izod Impact Strength 73°F (23°C), Injection Molded	43 ft·lb/in ²	90 kJ/m ²	ISO 180
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate	< 3.9 in/min	< 100 mm/min	ISO 3795
Flame Rating	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	140 to 176 °F	60 to 80 °C

Notes

¹ Typical values are not to be construed as specifications.

² ± 0.03
