



LubriOne™ NY-30GF/02M

Polyamide 6

Key Characteristics

Product Description

LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.

General

Material Status	• Commercial: Active		
Regional Availability	• Europe		
Features	• Low Friction	• Lubricated	• Wear Resistant
Uses	• Appliance Components	• Consumer Applications	• Printer Parts
	• Automotive Applications	• Conveyor Parts	• Pulleys
	• Bearings	• Gears	• Rollers
	• Business Equipment	• Industrial Applications	
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.34 to 1.38 g/cm ³	1.34 to 1.38 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.16E+6 psi	8000 MPa	ISO 527-2
Tensile Stress	21800 psi	150 MPa	ISO 527-2
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2
Flexural Stress	30500 psi	210 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	4.8 ft-lb/in ²	10 kJ/m ²	ISO 179
Unnotched Izod Impact Strength (73°F (23°C))	29 ft-lb/in ²	60 kJ/m ²	ISO 180
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	401 °F	205 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	392 °F	200 °C	ISO 75-2/A
Melting Temperature (DSC)	419 to 437 °F	215 to 225 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index	500 V	500 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 hr	3.0 hr
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	122 to 194 °F	50 to 90 °C