



LubriOne™ PC-000/10T NC008

Polycarbonate

Key Characteristics

Product Description	
PTFE lubricated	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Additive	• PTFE Lubricant
Features	• Lubricated
Appearance	• Natural Color
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.25	1.25	ASTM D792
Molding Shrinkage - Flow	5.0E-3 to 8.0E-3 in/in	0.50 to 0.80 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	7980 psi	55.0 MPa	ASTM D638
Flexural Modulus ³	334000 psi	2300 MPa	ASTM D790
Flexural Strength ³	13100 psi	90.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	3.7 ft-lb/in	200 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	264 °F	129 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	248 to 266 °F	120 to 130 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	554 to 590 °F	290 to 310 °C
Middle Temperature	554 to 590 °F	290 to 310 °C
Front Temperature	554 to 590 °F	290 to 310 °C
Mold Temperature	194 to 230 °F	90 to 110 °C

Injection Notes	
Injection Pressure: MED-HIGH	
Hold Pressure: MED-HIGH	
Screw Speed: MODERATE	
Back Pressure: LOW	

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (50 mm/min)

³ 0.051 in/min (1.3 mm/min)



Beyond Polymers.

Better Business Solutions.SM