



# LubriOne™ SF-25GF/10T

## Polyphenylene Sulfide

### Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Europe	
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight	• PTFE Micropowder, 10% Filler by Weight	
Features	• Good Impact Resistance • Good Stiffness • Good Strength	• Heat Stabilized • Low Friction • Lubricated	• Wear Resistant
Uses	• Appliances • Automotive Applications	• Consumer Applications • Electrical/Electronic Applications	• General Purpose • Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density <sup>2</sup>	1.60 g/cm <sup>3</sup>	1.60 g/cm <sup>3</sup>	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.31E+6 psi	9000 MPa	ISO 527-2/1
Tensile Stress	16000 psi	110 MPa	ISO 527-2/5
Tensile Strain (Break)	2.0 %	2.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	2.6 ft-lb/in <sup>2</sup>	5.5 kJ/m <sup>2</sup>	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature (DSC)	572 to 626 °F	300 to 330 °C	ISO 3146
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.031 in (0.8 mm)	V-0	V-0	
0.06 in (1.6 mm)	V-0	V-0	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	248 to 284 °F	120 to 140 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	599 to 617 °F	315 to 325 °C
Middle Temperature	608 to 626 °F	320 to 330 °C
Front Temperature	617 to 635 °F	325 to 335 °C
Nozzle Temperature	626 to 644 °F	330 to 340 °C
Mold Temperature	275 to 311 °F	135 to 155 °C

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> ±0.02

---



*Beyond Polymers.*

*Better Business Solutions. SM*